

POWEROIL TO 1020 60 H

POWEROIL TO 1020 60 H is a Type B, TVBU Uninhibited Transformer Oil meeting IEC 60296 : 2020 Edition 5.0 Standard Table – 4 General Specifications. It also meets the ASTM D 1275 Test requirement for Corrosive Sulphur.

Sr No	Characteristics	Unit	Test Method	Guaranteed Data	
				Min	Max
1	Appearance		Visual inspection of oil sample in transmitted light under a thickness of 10 cm at ambient temperature	Clear free from sediment and suspended matter	
2	Color		ISO 2049		1.5
3	Density at 20 ° C	g /ml	ISO 3675 or IEC 12185		0.895
4	Kinematic Viscosity at 40 ° C	mm ² / sec	ISO 3104 or ASTM D 7042		12
	at - 30 ° C				1800
5	Flash Point, PMCC	° C	ISO 2719	135	
6	Pour Point	° C	ISO 3016		- 40
7	Inter Facial Tension at 25 ° C	mN / m	ASTM D 971	40	
8	Acidity	mg KOH/ g	IEC 62021-1 or IEC 62021-2		0.01
9	Water Content, Bulk/ Drum, IBC	mg / kg	IEC 60814		30 / 40
10	Breakdown Voltage		IEC 60156		
	As Delivered / After Treatment	kV		30 / 70	
11	Dielectric Dissipation Factor (Tan δ) at 90 ° C & 40 to 60 Hz		IEC 60247 or IEC 61620		0.005
12	Corrosive Sulphur Silver Strip, 100 ° C, 18 Hrs. Copper Strip , 150 ° C, 48 Hrs.		DIN 51353 ASTM D 1275	Not Corrosive Not Corrosive	
13	Potentially Corrosive Sulphur		IEC 62535	Not Corrosive	
14	DBDS	mg / kg	IEC 62697-1	Not Detectable (< 5 mg/kg)	
15	Inhibitors according to IS 13631 / IEC 60666	%	IEC 60666	(U) Uninhibited Oil Not Detectable (< 0.01 %)	
16	Metal Passivator additives according to IS 13631 / IEC 60666	mg / kg	IEC 60666	Not Detectable (< 5 mg/kg)	
17	Other Additives			Does not contain any additives	
18	Oxidation Stability at 120 ° C, 164 Hrs.		IEC 61125 (Method C)		
	Total Acidity	mg KOH /g	4.8.4 of IEC 61125 : 2018		1.2
	Sludge	%	4.8.1 of IEC 61125 : 2018		0.8
	DDF at 90 ° C		4.8.5 of IEC 61125 : 2018		0.500
19	PCA Content	%	IP 346		3
20	PCB Content	mg / kg	IEC 61619	Not Detectable (< 2mg /kg)	

Disclaimer: APAR makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.

21	2 – Furfural and related compounds content	mg / kg	IEC 61198	Not Detectable (< 0.05 mg/kg) for each individual compound
----	--------------------------------------------	---------	-----------	-------------------------------------------------------------