

POWEROIL TOPAZ H 350 PRIME

Meets the requirements of the following specifications:

- USA FDA 21 CFR 178.3620 (b), technical white oils
- Europe Regulation (EU) 10/2011 on plastic material and articles intended to come into contact with foodstuff, White mineral oil.

Sr No	Characteristics	Test Method	Typical Values	Specification	
				Min	Max
1	Appearance	Visual		Clear & Bright	
2	Odour	Olfactory		Absent	
3	Color, Saybolt	ASTM D 6045		+ 30	-
4	Density at 25°C, gm/ml	ASTM D 1298		0.845	0.870
5	Kinematic Viscosity at 40°C, cSt	ASTM D 445 ASTM D7042		66	71
6	Kinematic Viscosity at 100°C, cSt	ASTM D 445 ASTM D 7042		8.5	-
7	Flash Point, (COC), °C	ASTM D 92		240	-
8	Pour Point, °C	ASTM D 97		-	-9
9	Average Molecular Weight	ASTM D 2502		480	-
10	Hydrocarbon with less than 25 carbons, wt %	ASTM D 6352		-	5
11	Color, Saybolt (After UV exposure for 48 Hrs.)	INHOUSE		+18	-
12	Volatility @ 10 mm Hg, temp (°C) at which	ASTM D 1160			
	5 % off		272	270	-
	10 % off		284	280	-
13	Paraffinic / Naphthenic / Aromatic	ASTM D 2140	68/32/0	-	-

Applications

Poweroil Topaz H 350 Prime is a purified mixture of liquid saturated hydrocarbons. It is colourless, transparent, and odourless.. Due to its low-volatility and high UV stability is suitable for special polymer applications.



Tomorrow's solutions today

Petroleum Specialities FZE

Wholly owned subsidiary of Apar Industries Ltd.

POWEROIL®

Powering Ahead

Poweroil Topaz H 350 Prime due to its very low volatility, excellent UV stability is suitable for applications such as Thermoplastic Elastomers/ Plastics/Adhesives/ Rubbers.

Disclaimer: APAR makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility. Website: www.apar.com

Product Data Sheet
Version # 1, 1st January , 2024